



# BEOGRADE 05 BTL023

## Material Technical Data Sheet

Date of issue: 23/07/2021 Version: 2.0

### SECTION 1: Identification of the substance/mixture and of the company/undertaking

#### 1.1. Product identifier

Product form	: Granulate
Name	: Beograde 05 BTL025
Product code	: 0595070023
Application	: Bottle blowing
Composition	: 5% Wood fibres + 95% biodegradable and compostable compound and additives

#### 1.2. Details of the supplier of the material specification sheet

##### Manufacturer

Beologic  
 Jolainstraat 44  
 8554 Sint-Denijs  
[info@beologic.com](mailto:info@beologic.com)

### SECTION 2: Physical, mechanical and thermal properties

#### 2.1. Information on basic physical, mechanical and thermal properties

Properties <sup>(1)</sup>	Method	Typical Value	Unit
<b>Composition / Physical</b>			
Content		Complex blend of biopolymers	
Renewable content		≥ 42	%
Colour material		Natural brown	
Coloured in mass		NO	
Transmission		Opaque	
Physical state		Solid	
Relative density	ISO 1183-1	1,25-1,35	g/cm <sup>3</sup>
UV package		NO	
Carbon footprint <sup>(2)</sup>	PAS 2050	*6,6959	Kg CO <sub>2</sub> Eq/ kg
Shelf life <sup>(3)</sup>		6	Months
<b>Mechanical</b>			
Tensile modulus	ISO 527	1140	MPa
Tensile strenght	ISO 527	18,8	MPa
Ultimate strain	ISO 527	8,3	%
Break stress	ISO 527	17,4	MPa
Elongation at break	ISO 527	250	%
Flexural modulus	ISO 178	1077	MPa
Flexural strength	ISO 178	27,5	MPa
Charpy impact strength	(Notched 1eA , 23 °C) ISO 179	32	kJ/m <sup>2</sup>
<b>Thermal</b>			
MFI	(190°C, 2.16 kg) ISO 1133-1	3-4	g/10min
Melting temperature range	ISO 11357-3	125-145	°C
HDT B	(0,45 MPa) ISO 75	57-60	°C
Decomposition temperature (TGA)	ISO 3451-1	300	°C
Ash content (TGA)	ISO 3451-1	≤ 5	%

(1) Typical properties; not to be construed as specifications.

(2) Carbon footprint calculated by Neutrologic

(3) Only if storage conditions were followed

\*Our Beograde grades are made carbon neutral by offsetting through certified climate projects.



# BEOGRADE 05 BTL023

## Material Technical Data Sheet

Date of issue: 23/07/2021 Version: 2.0

### 2.2. Processing conditions

Feed throat	60 – 60	°C
Feed temperature	160 – 170	°C
Compression zone	170 – 180	°C
Metering zone	180 – 185	°C
Die	180 – 190	°C

We recommend to use high injection speed. Short holding pressure and cooling times can be used.

#### General advice

Beograde is not compatible with a wide variety of other resins, and special purging sequences should be followed:

1. Before production, ensure to clean extruder and bring temperature to steady state with low viscosity, general purpose PP or PE.
2. Vacuum out hopper system to avoid contamination.
3. Introduce Beograde into the extruder at the operating conditions used in step one.
4. Once Beograde has purged, reduce barrel temperatures to desired set points.
5. At shutdown, purge machine with high viscosity polystyrene or polypropylene.

Purging time: approximately 10 to 20 minutes.

At higher temperature, the dwell time of the material inside the machine shall be reduced to a minimum in order to lower the risk of degradation. Don't leave the material hot inside the machine for long periods as the material will degrade.

### 2.3. Product Carbon footprint

The product carbon footprint helps to define the amount of greenhouse gas emissions generated by a product along its life cycle, it quantifies the ghg-emissions related to the production of our products.

Beologic calculates the carbon footprint of all sales products and this from cradle to gate.

The calculation of the carbon footprint is in accordance with the internationally recognized Greenhouse Gas Protocol Product Standard which is based on the standard ISO-14067 norm and PAS2050.

The carbon footprint is mentioned in our datasheet - by offsetting or compensating the calculated emissions we can present our products as Carbon Neutral compounds. This compensation is according the Verified Carbon Standard – more info via ([www.v-c-s.org](http://www.v-c-s.org)).

## SECTION 3: Drying conditions and storage

Beograde 05 BTL023 is a compound of biodegradable polymers (such as PLA). Residual moisture content can lead to hydrolysis degradation. **We recommend drying Beograde 05 BTL023 at 70°C for a period of 2 – 4 hours.** Don't overheat or dry it longer than recommended.

Residual moisture content (> 0.2%) can result in lower melt stability, surface mark or bubble formation during processing.

We recommend to store the material in dry conditions below 50°C and protected from UV-light. Opened bigbag should be used immediately or adequately sealed back up after use to avoid moisture uptake and have negative effects on the physical properties of the product. It is recommended to use Beograde granules within a time period of maximum 6 months.

Finished product made from Beograde should be stored dry and cold. Storage time and lifetime of finished products depends on processing parameters and on storage conditions (moisture, UV radiation ...).

## SECTION 4 Biodegradability and compostability

Beograde 05 BTL023 fulfills the requirements of the existing standards for compostable and biodegradable polymers (EN 13432), because it can be degraded by microorganisms.

As the compostability of the end product is dependent on the geometry of product, it is the responsibility of the manufacturer of the end product to ensure compliance with the regulations.

## SECTION 5: Food regulation

Beograde 05 BTL023 complies in its composition with the European food stuff legislation for food contact, EU Directive 10/2011/EC (and the amendments 2018/213 and 2018/831).

The material also complies with the US food contact notification for the main components: e.g. FCN 178, 475 and 907. A detailed food law status can be given on request. Whether the article is suitable for the application, has to be checked by the converter or packer.



# BEOGRADE 05 BTL023

## Material Technical Data Sheet

Date of issue: 23/07/2021 Version: 2.0

The technical data above are based on our current knowledge and experience. They do not release from the obligation to make one's own evaluation and trials, in respect to a variety of possible influences in processing and application of the product. A legally binding guarantee of certain properties or suitability for a special kind of application cannot be derived from the data.